



PERFORMANCE GRADE BITUMEN PG 70 E -22

AASHTO M332-23



CHARACTERISTICS	TEST METHOD	UNIT	AASHTO M332-23
Original Binder			
Flash point	AASHTO T48	°C	>230
Viscosity @ 135 °C	AASHTO T316	Pa.s	<3.0
Dynamic Shear, $G^*/\sin \delta$ @ 70°C 10 rad/s	AASHTO T315	kPa	>1.0
Rolling thin Film Oven (RTFOT Residue)			
Mass Change	AASHTO T240	%	<1.0
Dynamic Shear, $G^*/\sin \delta$ @ 70°C 10 rad/s	AASHTO T315	kPa	>2.2
MSCR Extremely Heavy Traffic, "E" Jnr3,2 @ 70°C	AASHTO T350	kPa ⁻¹	0.5
Pressure Aging Vessel (PAV) Residue (RTFOT + PAV) (20h, 2.1 Mpa), 100 °C			
Dynamic Shear, $G^*/\sin \delta$ @ 28°C 10 rad/s	AASHTO T315	kPa	<6000
BBR S @ 60 s, -12°C	AASHTO T313	MPa	<300
BBR m-value @ 60 s, -12°C	AASHTO T313	MPa	>0.300



epbitumen.com

The information and, in particular, the recommendations relating to the application and end use of EP Bitumen products are given in good faith on the basis of EP Bitumen's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with EP Bitumen's recommendations. In practice, differences in materials, substrates and actual site conditions are such that no warranty as to merchantability or fitness for a particular purpose, nor any liability arising from any legal relationship, from any written recommendation, or from any other advice given, can be inferred from this information. The user of the product must prove the suitability of the product for the intended application and purpose. EP Bitumen reserves the right to modify the properties of its products. Proprietary rights of third parties must be respected. All orders are accepted subject to our current terms of sale and delivery. Users should always consult the most recent edition of the local product data sheet for the product in question, copies of which will be provided on request.

PRODUCT DATA SHEET